



510 Gilmore Ave., Suite C
 Stockton, CA 95203
 Toll-free: 800-590-PLAS
 Phone: 209-464-2701
 Fax: 209-464-5760

MATERIAL WEIGHT - lbs. per square foot

MATERIAL		THICKNESS IN INCHES																							
		.375	.500	.625	.750	.875	1.000	1.125	1.250	1.375	1.500	1.750	2.000	2.250	2.500	2.750	3.000	3.250	3.500	3.750	4.000	4.250	4.500	4.750	5.000
ACETAL / DELRIN®	Nat, Blk	2.920	3.860	4.800	5.740	6.680	7.620	8.573	9.500	10.478	11.380	13.260	15.140	17.110	18.990	20.870	22.750	24.765	26.510	28.575	30.280	32.385	34.290	36.195	37.890
	20% GF	-	4.175	5.219	6.263	7.306	8.349	9.394	10.438	11.481	12.525	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	AF Blend	3.100	4.100	5.069	6.110	7.096	8.110	9.124	10.090	11.151	12.050	14.193	16.040	-	-	-	-	-	-	-	-	-	-	-	-
	SD	2.730	3.620	4.469	5.380	6.256	7.150	8.044	8.910	9.831	10.670	12.440	14.200	-	-	-	-	-	-	-	-	-	-	-	-
HALAR® 902	Natural	3.431	4.575	5.719	6.863	8.006	9.152	10.294	11.438	12.581	13.725	16.013	18.300	20.588	22.875	25.163	27.450	-	-	-	-	-	-	-	-
NYLON	Nat, Blk Trogamid	2.380	3.140	3.910	4.680	5.440	6.210	6.986	7.740	8.539	9.280	10.810	12.340	13.973	15.490	17.078	18.550	20.180	21.735	23.288	24.680	-	-	-	-
	MD	2.400	3.170	3.950	4.720	5.500	6.270	7.054	7.820	8.621	9.370	10.910	12.460	-	-	-	-	-	-	-	-	-	-	-	-
PBT	Natural	2.610	3.480	4.350	5.220	6.090	6.958	7.830	8.700	9.570	10.440	-	-	-	-	-	-	-	-	-	-	-	-	-	-
PEEK™	Nat, Blk	2.710	3.580	4.540	5.330	6.210	7.080	7.965	8.910	9.735	10.570	12.320	14.070	-	-	-	-	-	-	-	-	-	-	-	-
	30% GF	3.010	4.015	5.019	6.023	7.026	8.028	9.034	10.038	11.041	12.045	-	-	-	-	-	-	-	-	-	-	-	-	-	-
	Bearing Grade	2.891	3.855	4.819	5.783	6.746	7.707	8.674	9.638	10.601	11.565	-	-	-	-	-	-	-	-	-	-	-	-	-	-
POLYCARBONATE	Nat, Blk	2.480	3.300	4.075	4.910	5.705	6.520	7.335	8.120	8.965	9.730	11.340	12.950	14.640	16.190	17.860	19.430	21.160	22.680	24.290	25.900	-	-	-	-
	10% GF	2.550	3.400	4.250	5.100	5.950	6.797	7.650	8.500	9.350	10.200	11.900	13.600	15.300	17.000	-	-	-	-	-	-	-	-	-	-
	20% GF	2.723	3.630	4.538	5.445	6.353	7.257	8.168	9.075	9.983	10.890	12.705	14.520	16.335	18.150	-	-	-	-	-	-	-	-	-	-
POLYSULFONE	Nat, Blk	2.490	3.320	4.150	4.980	5.810	6.637	7.470	8.300	9.130	9.960	11.620	13.280	14.940	16.600	18.260	19.920	21.580	23.240	24.900	26.560	-	-	-	-
PPO / NORYL®	Blk EN265	2.210	2.950	3.688	4.425	5.163	5.900	6.638	7.380	8.110	8.540	9.950	11.800	13.275	14.750	16.230	17.800	19.180	20.340	21.750	23.600	-	-	-	-
	GFN3	2.588	3.450	4.313	5.175	6.038	6.904	7.763	8.625	9.488	10.350	12.075	13.800	15.525	17.250	18.975	20.700	-	-	-	-	-	-	-	-
PPS	Natural	2.790	3.700	4.563	5.500	6.388	7.300	8.213	9.125	10.038	10.950	12.775	14.600	-	-	-	-	-	-	-	-	-	-	-	-
	40% GF	-	4.415	5.519	6.623	7.726	8.831	9.934	11.038	12.141	13.245	15.453	17.660	-	-	-	-	-	-	-	-	-	-	-	-
PVDF	Nat, Blk	3.592	4.760	5.950	7.140	8.330	9.530	10.720	11.910	13.100	14.290	16.670	19.060	21.440	23.820	26.200	28.590	30.970	33.350	35.730	38.120	40.500	42.880	45.260	47.650
RADEL®	Nat, Blk	2.677	3.535	4.484	5.252	6.106	6.979	7.852	8.787	9.596	10.433	12.150	13.877	15.703	17.412	19.190	20.887	22.664	24.311	26.028	27.755	-	-	-	-
ULTEM®	Nat, Blk	2.650	3.500	4.440	5.200	6.046	6.910	7.774	8.700	9.501	10.330	12.030	13.740	15.548	17.240	19.000	20.680	22.440	24.070	25.770	27.480	-	-	-	-
	10% GF	-	3.585	4.481	5.378	6.274	7.172	8.066	8.963	9.859	10.755	12.548	14.340	-	-	-	-	-	-	-	-	-	-	-	-
	20% GF	-	3.800	4.750	5.700	6.650	7.600	8.550	9.500	10.450	11.400	-	-	-	-	-	-	-	-	-	-	-	-	-	-

TOLERANCES	
THICKNESS	+0.025" -0.000"
WIDTH	+0.250" -0.000"
LENGTH	+0.500" -0.000"

- Delrin is a registered tradename of Dupont
- Noryl and Ultem are registered trademarks of General Electric
- Radel is a registered trademark of Solvay Advanced Polymers, LLC
- Halar is a registered trademark of Solvay Solexis, Inc