



3837 Imperial Way  
Stockton CA, 95215  
Phone: 1-800-590-PLAS  
Fax: 209-464-5760

## Semilon PK5000 Typical Properties

### PEEK, Vestakeep® 5000G

Category	Property	Test Method	Units	Values
Mechanical	Specific Gravity, 73°F	D792	g/cm3	1.30
	Tensile Strength, 73°F Yield	D638	psi	14000
	Tensile Modulus of Elasticity, 73°F	D638	ksi	500
	Tensile Elongation (at break), 73°F	D638	%	>100
	Flexural Strength, 73°F	D790	psi	21000
	Flexural Modulus of Elasticity, 73°F	D790	ksi	550
	Shore D		D	87
	Coefficient of Friction (Dry vs. Steel) Dynamic	QTM 55007	-	n/a
Thermal	Coefficient of Linear Thermal Expansion (-40°F to 300°F)	D696	in./in./°F	3.3E-05
	Heat Deflection Temperature 264 psi	D648	°F	n/a
	Tg-Glass Transition	D3418	°F	n/a
	Melting Point Peak	D3418	°F	644
	Continuous Service Temperature in Air (Max.)	-	°F	480
	Thermal Conductivity	F433	BTU in./hr.ft.²°F	n/a
	Flammability @ 3.1 (1/8")	UL 94	-	V-0
Electrical	Dielectric Strength, Short Term	D149	Volts/mil	640
Chemical	Water Absorption Immersion, Saturation	D570	% by wt.	0.5
	Water Absorption (24 Hours @ 23°C/73°F)	D570	%	0.1

\*Typical values only. Actual properties of individual batches will vary within specification limits.